

# DATA SHEET THERMOLITE TYPE II

## DESCRIPTION

### Thermolite

Type II rabbeted insulation panel made with EPS beads plus a flame retardant.

For indoor and outdoor use: walls, foundations and under concrete floors.

## PRODUCT DATA

### Dimensions

> 2' x 8' x 1"	R-4
> 2' x 8' x 1 1/4"	R-5
> 2' x 8' x 1 7/8"	R-7,5
> 2' x 8' x 2 1/2"	R-10
> 4' x 8' x 1"	R-4
> 4' x 8' x 1 1/4"	R-5
> 4' x 8' x 1 7/8"	R-7,5
> 4' x 8' x 2 1/2"	R-10

Other sizes available on request.

## EVALUATION



- > Certified INTERTEK ETL SEMKO
- > Conforms to CAN/ULC-S701 standards
- > CCMC #12836-L

PHYSICAL PROPERTIES	IMPERIAL	METRIC	ASTM TEST	EPS TYPE 2
<b>Thermal resistance:</b> R-value at 75°F (24°C) for 1 in (25 mm) thickness	hr.ft <sup>2</sup> °F / BTU	m <sup>2</sup> °C / W	C-518 C-177	4.0 min. (0.70 min.)
Compressive strength (min.) at 10% distortion	psi	(kPa)	D-1621	16 (110)
Bending strength (min.)	psi	(kPa)	C-203	35 (240)
<b>Dimensional stability:</b> % of linear change (max.)	%	%	D-2126	1.5
Coefficient of thermal expansion (max.)	in/in/°F	(mm/mm/°C)	D-696	3.5x10 <sup>-5</sup> (6x10 <sup>-5</sup> C <sup>-1</sup> )
Water vapor permeability (max.)	Perm-inch	(ng/Pa.s.m <sup>2</sup> )	E-96	3.5 (200)
Water absorption (max.)	%	%	D-2842	4
<b>Effective temperature range:</b> > Continuous > Intermittent	°F °F	(°C) (°C)	- -	167 (75) 180 (82.2)
Flame spread rating	-	-	(CAN/ULC S102.2 M)	< 140
Generated smoke	-	-	(CAN/ULC S102.2 M)	< 380
Capillarity	-	-	-	Nil

## VALEUR ISOLANTE PERMANENTE GARANTIE

The thermal resistance of this type of insulation is permanent due to its cellular structure which contains only stabilized trapped air. EPS performance does not diminish over time.

## ECOLOGICAL

Contains no CFCs or HCFCs.

## NOTES

EPS beads should be considered flammable when subjected to a source of intense heat or a constant strong flame. They are vulnerable to petroleum-based solvents and prolonged exposure to ultraviolet radiation. EPS must therefore be covered according to the National Building Code.